



## Test Report

No. SL917192617004FW

Date: Sep 22, 2017

Page 1 of 3

SHANGHAI LANGFENG INDUSTRIAL CO, LTD  
ROOM 908, BUILDING 1, LUXIANG ROAD 111, BAOSHANG DISTRICT, SHANGHAI CHINA

The following samples were submitted and identified on behalf of the client as:

(A) Three pairs of safety shoes in black (B) six piece of steel insert plate.

Ref No.	:	M-8025
Size	:	42# 3 pairs safety shoes
Toecap	:	Steel Toe Cap
Insert Plate	:	Steel plate
Sole	:	Black PU / PU
Upper	:	Black cowhide leather
Vamp Lining	:	Black sandwich mes
Quarter Lining	:	Black sandwich mes
Tongue	:	Black cowhide leather
Collar	:	Black brace wed
Insole	:	Non-woven
Insock	:	Black sandwich mesh + EVA
Sample Receiving Date	:	Sep 19, 2017
Test Performing Period	:	Sep 19, 2017 ~ Sep 22, 2017
Test Performed	:	Selected test(s) as requested by applicant against ASTM F2413-11 performance standard.

\* \* \* \*

Test Results : Please refer to the next page(s).

Signed for and on behalf of  
SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Hanson Chen  
Account Supervisor



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)  
198 Kezhu Road, Sciencetech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86-20) 82155555 f (86-20) 82075169 www.sgsgroup.com.cn  
中国·广州·经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075169 e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)



**Test result:**
**Impact Resistance (ASTM F2412-11, Clause 5)**

Sample A

Size		Interior Height Clearance (mm)	ASTM F2413-11 Requirement	Pass/Fail
9	Right	16.2	Min. 12.7 mm	Pass
	Left	18.5		Pass
	Right	18.1		Pass

**Compression Resistance (ASTM F2412-11, Clause 6)**

Sample A

Size		Interior Height Clearance (mm)	ASTM F2413-11 Requirement	Pass/Fail
9	Left	20.2	Min. 12.7 mm	Pass
	Right	19.7		Pass
	Left	20.1		Pass

**Puncture Resistance (ASTM F2412-11, Clause 11)**

Sample B

Specimen	Test Result	ASTM F2413-11 Requirement	Pass/Fail
1	No Visually Penetration	*	Pass
2	No Visually Penetration		Pass
3	No Visually Penetration		Pass

Remark: \* = When Viewed At 90°Angle, The Tip Of The Test Pin Does Not Visually Penetrate Beyond The Face Of The Material Nearest The Foot, After An Applied Force Of 1200 N





### Sample



\*\*\* End of Report \*\*\*